



PANEL INSTALLATION SHOWN
 Mortar: Western W-5 (white)
 Joint Type: struck
 Size: h: 11 3/4", l: 23 3/4" - sandblasted finish



CUT STONE
TEXAS CREAM
PANELS, CUT STONE
& SLABS

GEOLOGY: limestone - quarried in USA

COLOR RANGE
 light buff to cream

COLOR CONSISTENCY PER BLOCK/SLAB
 consistent

WEIGHT CALCULATED IN INCHES
 $l \times w \times h / 1728$ (inches cubed) $\times 137$ = approx
 137 pounds per cubic foot

ASTM TESTING DATA

TEXAS CREAM C97 water absorption—6.13%
 TEXAS CREAM C97 density—136.8 pcf
 TEXAS CREAM C97 specific gravity—2.193
 TEXAS CREAM C99
 modulus of rupture—824 psi
 TEXAS CREAM C170
 compressive strength—6,560 psi



www.buechelstone.com

ARCHITECT/DESIGNER INFO
MATERIAL BANK

SKU: SM09018



BIM DETAILS

Revit, Hatch Patterns,
 Seamless Textures, 3-Part
 Specs, DWGS, SDS,
 Warranty



www.buechelstone.com

CUT STONE
TEXAS CREAM
PANELS, CUT STONE
& SLABS



COMMON APPLICATIONS

TEXAS CREAM

- ACCESSORIES _____
 (e.g. quoins, keystones, light mounts)
- BALUSTERS & COLUMNS _____
- DOOR & WINDOW SURROUNDS _____
- FIREPLACE SURROUNDS _____
- HEARTHES & MANTELS _____
- PIER CAPS _____
- SILLS _____