

## MOSAIC

### WHISPERING PINES FIELDSTONE



**GEOLOGY:** sandstone

#### BASIC USE

exterior walls of buildings and fireplaces  
stone shall be mortared in

#### COLOR RANGE

blue, green, and brown

#### COLOR CONSISTENCY PER PALLET

somewhat consistent

#### WEIGHT CALCULATED IN INCHES

l x w x h / 1728 (inches cubed) x 165  
= approx 165 pounds per cubic foot

#### PALLET

FULL VENEER: 3,000 pounds  
THIN VENEER: 10-15 lbs/ft<sup>2</sup>; Qty Bx or Sm Bx  
Qty Bx - 100 sq ft flats and 50 lineal ft corners  
Sm Bx - (24) 8 sq ft flats (192 sq ft) and  
(20) 8 lineal ft corners (160 lineal ft)



### FULL VENEER

#### COMMON COVERAGE \*Est.(can vary)

Standard Joint	Drystack	Overgrout
40 square feet / ton	30 ft <sup>2</sup> /ton	50 ft <sup>2</sup> /ton

#### WHISPERING PINES FIELDSTONE

##### DIMENSIONS

US: inches (average)	METRIC: mm (average)
----------------------	----------------------

l: 3" to 16" dia.	l: 76 to 406 dia.
-------------------	-------------------

h: 3" to 16" dia.	h: 76 to 406 dia.
-------------------	-------------------

w: 3" to 5" (4")	w: 76 to 127 (101)
------------------	--------------------

note: lengths and heights are irregular shapes  
3 inches to 16 inches in diameter

##### TYPICAL PIECE

ends irregular;  
natural split and rounded sides;  
bedface face and back;  
stone is random shapes

### PART NUMBERS

#### FULL VENEER

part number: 1BSTCAT01002TN

#### THIN VENEER

qty bx flat: 1BTVCAT01002QB  
sm bx flat: 1BTVCAT01002BX  
qty bx corner: 1BTVCAT01502QB  
sm bx corner: 1BTVCAT01502BX

### THIN VENEER

#### COMMON COVERAGE PER BOX \*Est.(can vary)

Standard Joint	Drystack	Overgrout
8 & 100 square feet	6 & 75 ft <sup>2</sup>	10 & 110 ft <sup>2</sup>

#### WHISPERING PINES FIELDSTONE

##### DIMENSIONS

US: inches (average)	METRIC: mm (average)
----------------------	----------------------

l: 3" to 12" dia.	l: 76 to 304 dia.
-------------------	-------------------

h: 3" to 12" dia.	h: 76 to 304 dia.
-------------------	-------------------

w: 3/4" to 1-1/4" (1")	w: 19 to 31 (25)
------------------------	------------------

corner return 3" to 5" cr: 76 to 127  
note: lengths and heights are irregular shapes  
3 inches to 12 inches in diameter

##### TYPICAL PIECE

ends irregular;  
natural split and rounded sides;  
bedface face and sawn back;  
stone is random shapes

### ASTM TESTING DATA

#### WHISPERING PINES C97

water absorption—0.96%

#### WHISPERING PINES C97

specific gravity—2.65

#### WHISPERING PINES C99

modulus of rupture—4,550 psi

#### WHISPERING PINES C170

compressive strength—11,630 psi

#### WHISPERING PINES C880

flexural strength—2,120 psi



www.buechelstone.com