

BLUESTONE

testing data

Stone type	Sandstone	
ASTM C97	Water Absorption	1,57%
ASTM C170	Compressive Strength w/ Rift	10,200 psi
	Compressive Strength Across Rift	17,400 psi
ASTM C880	Flexural Strength w/ Rift	1,600 psi
	Flexural Strength Across Rift	2,120 psi
ASTM C241-90	Abrasion Resistance	28



Natural Stone

800.236.4473

www.buechelstone.com