



## STEPS

### FOND DU LAC SNAPPED STEPS



**GEOLOGY:** dolomitic limestone

#### BASIC USE

for steps

#### COLOR RANGE

gray, light gray to white, buff

#### COLOR CONSISTENCY PER PALLET

consistent

#### WEIGHT CALCULATED IN INCHES

$l \times w \times h / 1728$  (inches cubed)  $\times 170$   
= approx 170 pounds per cubic foot

#### PALLET

4,000 pounds

#### STEPS PER PALLET

18" x 36" = 8 steps per pallet  
24" x 36" = 5 steps per pallet  
18" x 48" = 6 steps per pallet  
24" x 48" = 5 steps per pallet  
18" x 60" = 5 steps per pallet

## SNAPPED STEPS

### COVERAGES

coverages calculated as specified per project

#### FOND DU LAC 18"x36" SNAPPED STEPS

##### DIMENSIONS

###### US: inches

l: 35" to 37"

h: 5" to 8"

w: 17" to 19"

note:  $\pm 2"$  on split lengths and widths

note:  $\pm 3"$  on natural cleft height

###### METRIC: mm

l: 889 to 939 mm

h: 127 to 203 mm

w: 431 to 482 mm

#### FOND DU LAC 24"x36" SNAPPED STEPS

##### DIMENSIONS

###### US: inches

l: 35" to 37"

h: 5" to 8"

w: 23" to 25"

note:  $\pm 2"$  on split lengths and widths

note:  $\pm 3"$  on natural cleft height

###### METRIC: mm

l: 889 to 939 mm

h: 127 to 203 mm

w: 584 to 635 mm

#### FOND DU LAC 18"x48" SNAPPED STEPS

##### DIMENSIONS

###### US: inches

l: 47" to 49"

h: 5" to 8"

w: 17" to 19"

note:  $\pm 2"$  on split lengths and widths

note:  $\pm 3"$  on natural cleft height

###### METRIC: mm

l: 1193 to 1244 mm

h: 127 to 203 mm

w: 431 to 482 mm

## PART NUMBERS

part number 18"x36": 1STEBUE02001EA

part number 24"x36": 1STEBUE02006EA

part number 18"x48": 1STEBUE02002EA

part number 24"x48": 1STEBUE02004EA

part number 18"x60": 1STEBUE02014EA

## SNAPPED STEPS

### FOND DU LAC 24"x48" SNAPPED STEPS

#### DIMENSIONS

##### US: inches

l: 47" to 49"

h: 5" to 8"

w: 23" to 25"

note:  $\pm 2"$  on split lengths and widths

note:  $\pm 3"$  on natural cleft height

##### METRIC: mm

l: 1193 to 1244 mm

h: 127 to 203 mm

w: 584 to 635 mm

#### TYPICAL PIECE

ends square;

natural cleft top and bottom;

split sides, face and back;

stone is rectangular;

custom sizing by request

## ASTM TESTING DATA

FOND DU LAC C97 water absorption—0.36%

FOND DU LAC C97 density—174.2 pcf

FOND DU LAC C99

modulus of rupture—1,470 psi

FOND DU LAC C170

compressive strength w/rift—29,040 psi

compressive strength across rift—34,240 psi

FOND DU LAC C880

flexural strength—1,740 psi



www.buechelstone.com