

GRANITE COBBLES & SPLIT GRANITE FIELDSTONE

testing data

ASTM C97	Water Absorption	0.15%
ASTM C97	Specific Gravity	2.6 to 2.81
ASTM C97	Density	163.34 pcf
ASTM C170	Compressive Strength	20,731 psi
ASTM C880	Flexural Strength	1,681 psi
ASTM C241	Abrasion Resistance	80.46



Natural Stone

800.236.4473

www.buechelstone.com