

## PATIO & PAVING

MILL CREEK  
PATTERNED  
FLAGSTONE -  
THERMALLED



**GEOLOGY:** limestone

### BASIC USE

on patios and walkways; stone is dryset in gravel (screenings) bed or mortared in

### COLOR RANGE

wide mottled range of gray, pink, and tan; color variations common within a piece

### COLOR CONSISTENCY PER PALLET

inconsistent

### WEIGHT CALCULATED IN INCHES

l x w x h / 1728 (inches cubed) x 170  
= approx 170 pounds per cubic foot

### PALLET

as specified per project

## PATIO & PAVING

**COMMON COVERAGE** \*Est.(can vary)

2" height

80 square feet / ton

MILL CREEK PATTERNED  
FLAGSTONE-THERMALLED

### DIMENSIONS

US: inches

l: 6" to 24"

h: 2"

w: 6" to 24"

note: ± 1/8" on sawn sides

METRIC: mm

l: 152 to 609 mm

h: 51 mm

w: 152 to 609 mm

## PART NUMBERS

part number: N/A

## PATIO & PAVING

MILL CREEK PATTERNED  
FLAGSTONE-THERMALLED

### TYPICAL PIECE

ends square;

sawn and thermalled top;

sawn sides, face, and back;

natural cleft bottom;

stone is squares and rectangles

## ASTM TESTING DATA

MILL CREEK C97 water absorption—0.66%

MILL CREEK C97 density—173.0 pcf

MILL CREEK C99

modulus of rupture—2,072 psi

MILL CREEK C170

compressive strength—26,260 psi

MILL CREEK C880 flexural strength—1,374 psi



www.buechelstone.com