



LEDGESTONE

**FOND DU LAC
LEDGESTONE**

GEOLOGY: dolomitic limestone

BASIC USE

exterior walls of buildings and fireplaces
stone shall be mortared in

COLOR RANGE

gray, light gray,
buff, and white

COLOR CONSISTENCY PER PALLET

somewhat consistent

WEIGHT CALCULATED IN INCHES

l x w x h / 1728 (inches cubed) x 170
= approx 170 pounds per cubic foot

PALLET

FULL VENEER: 4,000 pounds
THIN VENEER: 10-15 lbs/ft²; Qty Bx or Sm Bx
Qty Bx - 100 sq ft flats and 50 lineal ft corners
Sm Bx - (24) 8 sq ft flats (192 sq ft) and
(20) 8 lineal ft corners (160 lineal ft)

FULL VENEER

COMMON COVERAGE *Est.(can vary)

Standard Joint	Drystack	Overgrout
40 square feet / ton	30 ft ² /ton	50 ft ² /ton

FOND DU LAC LEDGESTONE

DIMENSIONS

US: inches (average) **METRIC: mm (average)**

l: 4" to 16" (8")	l: 102 to 406 (203)
h: 3/4" to 2-1/4"	h: 19 to 57
w: 3" to 5" (4")	w: 76 to 127 (101)

TYPICAL BLEND

up to 30 percent may be sawn top and bottom with a bedface face;
face of stone cannot have a sawn finish
TYPICAL PIECE

ends random;
natural cleft top and bottom;
face and sides natural split or seamface;
back sawn; stone is linear

PART NUMBERS

FULL VENEER

part number: 1BSTBUE02044TN

THIN VENEER

qty bx flat: 1BTVBUE02048QB
sm bx flat: 1BTVBUE02048BX
qty bx corner: 1BTVBUE02548QB
sm bx corner: 1BTVBUE02548BX

THIN VENEER

COMMON COVERAGE PER BOX *Est.(can vary)

Drystack Joint	Standard Joint
8 & 100 square feet	10 & 110 ft ²

note: packaged for drystack install (8 & 100 ft²)

FOND DU LAC LEDGESTONE

DIMENSIONS

US: inches (average) **METRIC: mm (average)**

l: 4" to 16" (8")	l: 102 to 406 (203)
h: 3/4" to 2-1/4"	h: 19 to 57
w: 3/4" to 1-1/4" (1")	w: 19 to 38 (25)
corner return 3" to 5"	cr: 76 to 127

TYPICAL BLEND

up to 30 percent may be sawn top and bottom with a bedface face;
face of stone cannot have a sawn finish
TYPICAL PIECE

ends random;
natural cleft top and bottom;
face and sides natural split or seamface;
back sawn; stone is linear

ASTM TESTING DATA

FOND DU LAC C97 water absorption—0.36%
FOND DU LAC C97 density—174.2 pcf
FOND DU LAC C99
modulus of rupture—1,470 psi
FOND DU LAC C170
compressive strength w/rift—29,040 psi
compressive strength across rift—34,240 psi
FOND DU LAC C880
flexural strength—1,740 psi



www.buechelstone.com