



**LEDGESTONE**

**WHISPERING  
PINES  
LEDGESTONE**

**GEOLOGY:** sandstone

#### BASIC USE

exterior walls of buildings and fireplaces  
stone shall be mortared in

#### COLOR RANGE

greens, blues, and browns

#### COLOR CONSISTENCY PER PALLET

consistent

#### WEIGHT CALCULATED IN INCHES

$l \times w \times h / 1728$  (inches cubed)  $\times 165$   
= approx 165 pounds per cubic foot

#### PALLET

FULL VENEER: 3,000 pounds  
THIN VENEER: 10-15 lbs/ft<sup>2</sup>; Qty Bx or Sm Bx  
Qty Bx - 100 sq ft flats and 50 lineal ft corners  
Sm Bx - (24) 8 sq ft flats (192 sq ft) and  
(20) 8 lineal ft corners (160 lineal ft)

### FULL VENEER

#### COMMON COVERAGE \*Est.(can vary)

Standard Joint	Drystack	Overgrout
40 square feet / ton	30 ft <sup>2</sup> /ton	50 ft <sup>2</sup> /ton

#### WHISPERING PINES LEDGESTONE

##### DIMENSIONS

**US: inches (average)**    **METRIC: mm (average)**

l: 6" to 24" (12")    l: 152 to 609 (304)

h: 1" to 4"    h: 25 to 101

w: 3" to 5" (4")    w: 76 to 127 (101)

##### TYPICAL PIECE

ends random;  
natural cleft top and bottom;  
back, face, and sides split;  
stone is mostly rectangular

### PART NUMBERS

#### FULL VENEER

part number: 1BSTCAT01001TN

#### THIN VENEER

qty bx flat: 1BTVCAT01001QB  
sm bx flat: 1BTVCAT01001BX  
qty bx corner: 1BTVCAT01501QB  
sm bx corner: 1BTVCAT01501BX

### THIN VENEER

#### COMMON COVERAGE PER BOX \*Est.(can vary)

Drystack Joint	Standard Joint
8 & 100 square feet	10 & 110 ft <sup>2</sup>

note: packaged for drystack install (8 & 100 ft<sup>2</sup>)

#### WHISPERING PINES LEDGESTONE

##### DIMENSIONS

**US: inches (average)**    **METRIC: mm (average)**

l: 6" to 24" (12")    l: 152 to 609 (304)

h: 1" to 4"    h: 25 to 101

w: 3/4" to 1-1/4" (1")    w: 19 to 31 (25)

corner return 3" to 5"    cr: 76 to 127

##### TYPICAL PIECE

ends random;  
natural cleft top and bottom;  
face and sides split; back is sawn;  
stone is mostly rectangular

### ASTM TESTING DATA

#### WHISPERING PINES C97

water absorption—0.96%

#### WHISPERING PINES C97

specific gravity—2.65

#### WHISPERING PINES C99

modulus of rupture—4,550 psi

#### WHISPERING PINES C170

compressive strength—11,630 psi

#### WHISPERING PINES C880

flexural strength—2,120 psi



www.buechelstone.com