



**GEOLOGY:** dolomitic limestone

### BASIC USE

exterior walls of buildings and fireplaces  
stone shall be mortared in

### COLOR RANGE

light gray to white

### COLOR CONSISTENCY PER PALLET

consistent

### WEIGHT CALCULATED IN INCHES

$l \times w \times h / 1728$  (inches cubed)  $\times 170$   
= approx 170 pounds per cubic foot

### PALLET

FULL VENEER: 4,000 pounds  
THIN VENEER: 10-15 lbs/ft<sup>2</sup>; Qty Bx or Sm Bx  
Qty Bx - 100 sq ft flats and 50 lineal ft corners  
Sm Bx - (24) 8 sq ft flats (192 sq ft) and  
(20) 8 lineal ft corners (160 lineal ft)

## FULL VENEER

### COMMON COVERAGE \*Est.(can vary)

Standard Joint	Drystack	Overgrout
40 square feet / ton	30 ft <sup>2</sup> /ton	50 ft <sup>2</sup> /ton

### WHITE COUNTRY SQUIRE

#### DIMENSIONS

US: inches (average)	METRIC: mm (average)
l: 6" to 42" (14")	l: 152 to 1066 (355)
h: 1/2" to 8"	h: 13 to 203
w: 3" to 5" (4")	w: 76 to 127 (101)

sides of stone shall be no less than 2-1/2 inches in width; stone shall not vary in height more than 1/2 an inch in a 12 inch span

#### EXAMPLE

a stone that is 24 inches long could have a height of 6 inches on one end and 5 inches on the other end and be acceptable

#### TYPICAL PIECE

ends square;  
natural cleft top and bottom;  
back, face, and sides split;  
stone is mostly rectangular

## PART NUMBERS

### FULL VENEER

part number: 1BSTBUE02003TN

### THIN VENEER

qty bx flat: 1BTVBUE02003BX  
sm bx flat: 1BTVBUE02003QB  
qty bx corner: 1BTVBUE02503BX  
sm bx corner: 1BTVBUE02503QB

## THIN VENEER

### COMMON COVERAGE PER BOX \*Est.(can vary)

Standard Joint	Drystack	Overgrout
8 & 100 square feet	6 & 75 ft <sup>2</sup>	10 & 110 ft <sup>2</sup>

### WHITE COUNTRY SQUIRE

#### DIMENSIONS

US: inches (average)	METRIC: mm (average)
l: 6" to 24" (12")	l: 152 to 533 (304)
h: 1/2" to 8"	h: 13 to 203
w: 3/4" to 1-1/4" (1")	w: 19 to 31 (25)

corner return 3" to 5" cr: 76 to 127  
stone shall not vary in height more than 1/2 an inch in a 12 inch span

#### EXAMPLE

a stone that is 24 inches long could have a height of 6 inches on one end and 5 inches on the other end and be acceptable

#### TYPICAL PIECE

ends square;  
natural cleft top and bottom;  
face and sides split; back is sawn;  
stone is mostly rectangular

## ASTM TESTING DATA

FOND DU LAC C97 water absorption—0.36%  
FOND DU LAC C97 density—174.2 pcf  
FOND DU LAC C99  
modulus of rupture—1,470 psi  
FOND DU LAC C170  
compressive strength w/rift—29,040 psi  
compressive strength across rift—34,240 psi  
FOND DU LAC C880  
flexural strength—1,740 psi



www.buechelstone.com