



ASHLAR
SILVERDALE
COUNTRY SQUIRE

GEOLOGY: limestone- quarried in USA

COLOR RANGE

buffs, tans and creams, with occasional grays

COLOR CONSISTENCY PER PALLET
consistent

PALLET

FULL VENEER: 4,000 pounds
THIN VENEER: 10-15 lbs/ft²; Qty Bx or Sm Bx
Qty Bx-100 sq ft flats and 50 lineal ft corners
Sm Bx- (24) 8 sq ft flats (192 sq ft) and
(20) 8 lineal ft corners (160 lineal ft)

ASTM TESTING DATA

SILVERDALE C97 water absorption—7.27%
SILVERDALE C97 density—134.1 pcf
SILVERDALE C97 specific gravity—2.149
SILVERDALE C99
modulus of rupture—1,174 psi
SILVERDALE C170
compressive strength—6,631 psi
SILVERDALE C241 abrasion resistance—5.38
Solar Reflectance % ASTM C1549 57%
Thermal Emittance ASTM C1371 0.88
Solar Reflectance Index (12 W-M⁻²-K⁻¹) 67.82

PART NUMBERS

FULL VENEER:

1BSTKNS03007TN- Sold per Ton

THIN VENEER:

Qty Bx flat: 1BTVKNS03006QB - Sold per pallet

Sm Bx flat: 1BTVKNS03006BX- Sold per box

Qty Bx corner: 1BTVKNS03506QB- Sold per pallet

Sm Bx corner: 1BTVKNS03506BX- Sold per box

FULL VENEER

COMMON COVERAGE *Est.(can vary)
Standard Joint Drystack Overgrout
40 square feet / ton 30 ft²/ton 50 ft²/ton

DIMENSIONS

l: 6" to 42" (14")

h: 1/2" to 10"

w: 3" to 5" (4")

Stone ends shall be no less than 2-1/2" width

TYPICAL PIECE

Ends square; natural cleft top and bottom;
back, face and sides split;
stone is mostly rectangular.

THIN VENEER

COMMON COVERAGE PER BOX *Est.(can vary)
Standard Joint Drystack Overgrout
8 & 100 square feet 6 & 75 ft² 10 & 110 ft²

DIMENSIONS

l: 6" to 24" (12")

h: 1/2" to 8"

w: 3/4" to 1-1/4" (1")

corner return 3" to 5"

TYPICAL PIECE

Ends square; natural cleft top and bottom;
face and sides split; sawn back;
stone is mostly rectangular.

ARCHITECT/DESIGNER INFO

MATERIAL BANK

SKU: SM01030



INSTALLATION SHOWN

Mortar: Western Type S

Joint Type: Raked

BIM DETAILS

Revit, Hatch Patterns,
Seamless Textures, 3-Part
Specs, DWGS, SDS,
Warranty



www.buechelstone.com