

ASHLAR
SILVERDALE
COUNTRY
SQUIRE



GEOLOGY: limestone

BASIC USE

exterior walls of buildings and fireplaces
stone shall be mortared in

COLOR RANGE

light gray to buff with
occasional blue veins

COLOR CONSISTENCY PER PALLET

consistent

WEIGHT CALCULATED IN INCHES

l x w x h / 1728 (inches cubed) x 170
= approx 170 pounds per cubic foot

PALLET

FULL VENEER: 4,000 pounds
THIN VENEER: 10-15 lbs/ft²; Qty Bx or 5m Bx
Qty Bx- 100 sq ft flats and 50 lineal ft corners
5m Bx- (24) 8 sq ft flats (192 sq ft) and
(20) 8 lineal ft corners (160 lineal ft)

FULL VENEER

COMMON COVERAGE *Est.(can vary)

Standard Joint	Drystack	Overgrout
40 square feet / ton	30 ft ² /ton	50 ft ² /ton

COUNTRY SQUIRE

DIMENSIONS

US: inches (average)	METRIC: mm (average)
l: 6" to 42" (14")	l: 152 to 1066 (355)
h: 1/2" to 10"	h: 13 to 254
w: 3" to 5" (4")	w: 76 to 127 (101)

sides of stone shall be no less than 2-1/2 inches in width; stone shall not vary in height more than 1/2 an inch in a 12 inch span

EXAMPLE

a stone that is 24 inches long could have a height of 6 inches on one end and 5 inches on the other end and be acceptable

TYPICAL PIECE

ends square;
natural cleft top and bottom;
back, face and sides split;
stone is mostly rectangular occasional rustic



PART NUMBERS

FULL VENEER

part number: 1BSTKNS03007TN

THIN VENEER

qty bx flat: 1BTVKNS03006QB
sm bx flat: 1BTVKNS03006BX
qty bx corner: 1BTVKNS03506QB
sm bx corner: 1BTVKNS03506BX

THIN VENEER

COMMON COVERAGE PER BOX *Est.(can vary)

Standard Joint	Drystack	Overgrout
8 & 100 square feet	6 & 75 ft ²	10 & 110 ft ²

SILVERDALE COUNTRY SQUIRE

DIMENSIONS

US: inches (average)	METRIC: mm (average)
l: 6" to 24" (12")	l: 152 to 609 (304)
h: 1/2" to 10"	h: 13 to 254
w: 3/4" to 1-1/4" (1")	w: 19 to 31 (25)
corner return 3" to 5"	cr: 76 to 127

stone shall not vary in height more than 1/2 an inch in a 12 inch span

EXAMPLE

a stone that is 24 inches long could have a height of 6 inches on one end and 5 inches on the other end and be acceptable

TYPICAL PIECE

ends square;
natural cleft top and bottom;
face and sides split; back sawn
stone is mostly rectangular occasional rustic

ASTM TESTING DATA

SILVERDALE C97 water absorption—7.27%
SILVERDALE C97 density—134.1 pcf
SILVERDALE C97 specific gravity—2.149
SILVERDALE C99
modulus of rupture—1,174 psi
SILVERDALE C170
compressive strength—6,631 psi
SILVERDALE C241 abrasion resistance—5.38