



DIMENSIONAL
WHITE MARIGOLD
TAILORED BLEND

GEOLOGY: limestone

BASIC USE

exterior walls of buildings and fireplaces
stone shall be mortared in

COLOR RANGE

buffs, tans and white with occasional veining

COLOR CONSISTENCY PER PALLET

consistent

WEIGHT CALCULATED IN INCHES

l x w x h / 1728 (inches cubed) x 160
= approx 160 pounds per cubic foot

PALLET

FULL VENEER: 4,000 pounds
THIN VENEER: 10-15 lbs/ft²; Qty Bx or Sm Bx
Qty Bx- 100 sq ft flats and 50 lineal ft corners
Sm Bx- (24) 8 sq ft flats (192 sq ft) and
(20) 8 lineal ft corners (160 lineal ft)

FULL VENEER

COMMON COVERAGE *Est.(can vary)

Standard Joint	Drystack	Overgrout
40 square feet / ton	30 ft ² /ton	50 ft ² /ton

WHITE MARIGOLD TAILORED BLEND

DIMENSIONS

US: inches (average) METRIC: mm (average)

l: 6" to 42" (24") l: 152 to 1066 (609)

h: 2-1/4"; h: 5"; h: 57; h: 127;

h: 7-3/4"; h: 10-1/2" h: 196; h: 266

w: 3" to 5" (4") w: 76 to 127 (101)

note: ± 1/8" on sawn heights

ADDITIONAL SIZES

other custom heights available:

TYPICAL BLEND

20 percent 2-1/4"; 40 percent 5";

30 percent 7-3/4"; 10 percent 10-1/2"

TYPICAL PIECE

ends square;

sawn top and bottom; sides are split;

splitface face and back with occasional bedface;

stone is rectangular in appearance with length longer than height

PART NUMBERS

FULL VENEER

part number: 1BSTKNS01004TN

THIN VENEER

qty bx flat: 1BTVKNS01004QB

sm bx flat: 1BTVKNS01004BX

qty bx corner: 1BTVKNS01504QB

sm bx corner: 1BTVKNS01504BX

ASTM TESTING DATA

WHITE MARIGOLD C97 water absorption—9.43%
specific gravity — 2.042 to 2.066
density—125.1 lbs/ft³

WHITE MARIGOLD C170
dry perpendicular—5,490 psi
wet perpendicular—3,680 psi
dry parallel —4,530 psi
wet parallel—3,420 psi

WHITE MARIGOLD C880
flexural strength-wet —500 psi
flexural strength-dry —700 psi

WHITE MARIGOLD C1353
abrasion—3.5

WHITE MARIGOLD ANSI A326.3
friction—0.83



www.buechelstone.com