

LEDGESTONE

BLACK FROST LEDGESTONE



GEOLOGY: quartzitic sandstone- quarried in USA

COLOR RANGE

blacks, charcoals, grays, blues, whites with occasional greens, buffs, and browns

COLOR CONSISTENCY PER PALLET

somewhat consistent

PALLET

FULL VENEER: 4,000 pounds
THIN VENEER: 10-15 lbs/ft²; Qty Bx or Sm Bx
Qty Bx- 100 sq ft flats and 50 lineal ft corners
Sm Bx- (24) 8 sq ft flats (192 sq ft) and
(20) 8 lineal ft corners (160 lineal ft)

ASTM TESTING DATA

BLACK FROST C97

water absorption—0.2%

BLACK FROST C97

specific gravity—3.051

BLACK FROST C97

density—190.4 pcf

BLACK FROST C99

modulus of rupture dry—3,040 psi

modulus of rupture wet—2,610 psi

BLACK FROST C170

compressive strength parallel dry—15,070 psi

compressive strength parallel

wet—12,070 psi

compressive strength perpendicular

dry—25,340 psi

compressive strength perpendicular

wet—15,070 psi

PART NUMBER

FULL VENEER:

1BSTGRA03033TN - Sold per Ton

THIN VENEER:

Qty Bx flat: 1BTVGRA03033QB - Sold per pallet

Sm Bx flat: 1BTVGRA03033BX - Sold per box

Qty Bx corner: 1BTVGRA03533QB- Sold per pallet

Sm Bx corner: 1BTVGRA03533BX- Sold per box

ARCHITECT/DESIGNER INFO

MATERIAL BANK

SKU: SM05002



INSTALLATION SHOWN

Mortar: Laticrete MVIS

Joint Type: Drystack

BIM DETAILS

Revit, Hatch Patterns,
Seamless Textures, 3-Part
Specs, DWGS, SDS,
Warranty



FULL VENEER

COMMON COVERAGE *Est.(can vary)

Standard Joint	Drystack	Overgrout
35 square feet / ton	25 ft ² /ton	45 ft ² /ton

DIMENSIONS

l: 4" to 16" (8")

h: 1/2" to 3"

w: 3" to 5" (4")

TYPICAL PIECE

Ends random; natural cleft top and bottom;
natural splitface, splitface and seamface face;
sides natural split or seamface;
back split or sawn; stone is linear.

THIN VENEER

COMMON COVERAGE PER BOX *Est.(can vary)

Standard Joint	Drystack	Overgrout
8 & 100 square feet	6 & 75 ft ²	10 & 110 ft ²

DIMENSIONS

l: 4" to 16" (8")

h: 1/2" to 3"

w: 3/4" to 1-1/4" (1")

corner return 3" to 6"

TYPICAL PIECE

Ends random; natural cleft top and bottom;
natural splitface, splitface and seamface face;
sides natural split or seamface;
back sawn; stone is linear.