



FIELDLEDGE
KOHLER HERITAGE
BLEND

GEOLOGY: dolomitic limestone- quarried in USA

COLOR RANGE

grays, dark grays, charcoals, whites, tans, golds and buffs

COLOR CONSISTENCY PER PALLET

somewhat consistent

PALLET

FULL VENEER: 4,000 pounds
 THIN VENEER: 10-15 lbs/ft²; Qty Bx or Sm Bx
 Qty Bx-100 sq ft flats and 50 lineal ft corners
 Sm Bx- (24) 8 sq ft flats (192 sq ft) and
 (20) 8 lineal ft corners (160 lineal ft)

ASTM TESTING DATA

MILL CREEK C97 water absorption—0.51%
 MILL CREEK C97 density—172.6 pcf
 MILL CREEK C99
 modulus of rupture perpendicular —2,280 psi
 modulus of rupture parallel —860 psi
 MILL CREEK C170
 compressive strength—28,100 psi
 MILL CREEK C880 flexural strength—1,580 psi
 FOND DU LAC C97 water absorption—0.11%
 FOND DU LAC C97 density—176.5 pcf
 FOND DU LAC C99
 modulus of rupture—2,480 psi
 FOND DU LAC C170
 compressive strength w/rift—31,810 psi
 compressive strength across rift—26,550 psi
 FOND DU LAC C880
 flexural strength—1,740 psi

PART NUMBERS

FULL VENEER:

1BSTBUE02040TN- Sold per Ton

THIN VENEER:

Qty Bx flat: 1BTVBUE02040QB- Sold per pallet
 Sm Bx flat: 1BTVBUE02040BX- Sold per box
 Qty Bx corner: 1BTVBUE02540QB- Sold per pallet
 Sm Bx corner: 1BTVBUE02540BX - Sold per box

FULL VENEER

COMMON COVERAGE *Est.(can vary)

Standard Joint	Drystack	Overgrout
40 square feet / ton	30 ft ² /ton	50 ft ² /ton

DIMENSIONS

l: 6" to 24"
 h: 2" to 12"
 w: 3" to 5" (4")

note: lengths and heights can vary with rough irregular shapes mixed in.

TYPICAL PIECE

Ends random, completely random mix of Fond du Lac and Mill Creek material; rough cut stone is a mixture of splitface, natural splitface, and bedface; stone is mixture of square, rectangular, triangular, trapezoidal, and parallelogram shapes.

THIN VENEER

COMMON COVERAGE PER BOX *Est.(can vary)

Standard Joint	Drystack	Overgrout
8 & 100 square feet	6 & 75 ft ²	10 & 110 ft ²

DIMENSIONS

l: 6" to 24"
 h: 2" to 12"
 w: 3/4" to 1-1/4" (1")

corner return 3" to 6"
 note: lengths and heights can vary with rough irregular shapes mixed in.

TYPICAL PIECE

Ends random, completely random mix of Fond du Lac and Mill Creek material; rough cut stone is a mixture of splitface, natural splitface, and bedface; stone is mixture of square, rectangular, triangular, trapezoidal, and parallelogram shapes, back is sawn.

ARCHITECT/DESIGNER INFO

MATERIAL BANK

SKU: SM04013



INSTALLATION SHOWN

Mortar: Western Type- S
 Joint Type: Overgrout

BIM DETAILS

Revit, Hatch Patterns,
 Seamless Textures, 3-Part
 Specs, DWGS, SDS,
 Warranty



www.buechelstone.com