

ASHLAR

MILL CREEK
COUNTRY SQUIRE



GEOLOGY: dolomitic limestone- quarried in USA

COLOR RANGE
light gray to buff with occasional blue veins

COLOR CONSISTENCY PER PALLET
consistent

PALLET

FULL VENEER: 4,000 pounds
THIN VENEER: 10-15 lbs/ft²; Qty Bx or Sm Bx
Qty Bx- 100 sq ft flats and 50 lineal ft corners
Sm Bx- (24) 8 sq ft flats (192 sq ft) and
(20) 8 lineal ft corners (160 lineal ft)

ASTM TESTING DATA

MILL CREEK C97 water absorption—0.51%
MILL CREEK C97 density—172.6 pcf
MILL CREEK C99
modulus of rupture perpendicular —2,280 psi
modulus of rupture parallel —860 psi
MILL CREEK C170
compressive strength—28,100 psi
MILL CREEK C880 flexural strength—1,580 psi

PART NUMBER

FULL VENEER:

1BSTLENO1001TN- Sold per Ton

THIN VENEER:

Qty Bx flat: 1BTVLENO1001QB- Sold per pallet

Sm Bx flat: 1BTVLENO1001BX- Sold per box

Qty Bx corner: 1BTVLENO1501QB- Sold per pallet

Sm Bx corner: 1BTVLENO1501BX- Sold per box

ARCHITECT/DESIGNER INFO

MATERIAL BANK

SKU: SM01022



INSTALLATION SHOWN

Mortar: Western W-11

Joint Type: Raked

BIM DETAILS

Revit, Hatch Patterns,
Seamless Textures, 3-Part
Specs, DWGS, SDS,
Warranty



FULL VENEER

COMMON COVERAGE *Est.(can vary)

Standard Joint	Drystack	Overgrout
40 square feet / ton	30 ft ² /ton	50 ft ² /ton

DIMENSIONS

l: 6" to 42" (14")

h: 1/2" to 8"

w: 3" to 5" (4")

Stone Ends shall be no less than 2-1/2" width

TYPICAL PIECE

Ends square; natural cleft top and bottom;
back, face and sides split or seamface;
stone is mostly rectangular.

THIN VENEER

COMMON COVERAGE PER BOX *Est.(can vary)

Standard Joint	Drystack	Overgrout
8 & 100 square feet	6 & 75 ft ²	10 & 110 ft ²

DIMENSIONS

l: 6" to 24" (12")

h: 1/2" to 8"

w: 3/4" to 1-1/4" (1")

corner return 3" to 5"

TYPICAL PIECE

Ends square; natural cleft top and bottom;
face and sides split or seamface; back is sawn;
stone is mostly rectangular.