

# FIELDLEDGE

OILED NUBUCK  
SIENA



**GEOLOGY:** limestone- quarried in USA

### COLOR RANGE

buff, brown, tans, gray and black

### COLOR CONSISTENCY PER PALLET

somewhat consistent

### PALLET

FULL VENEER: 4,000 pounds

THIN VENEER: 10-15 lbs/ft<sup>2</sup>; Qty Bx or Sm Bx  
Qty Bx- 100 sq ft flats and 50 lineal ft corners  
Sm Bx- (24) 8 sq ft flats (192 sq ft) and  
(20) 8 lineal ft corners (160 lineal ft)

### ASTM TESTING DATA

C97 water absorption—7.27%

C97 density—134.1 pcf

C97 specific gravity—2.149

C99 modulus of rupture—1,174 psi

C170 compressive strength—6,631 psi

C241 abrasion resistance—5.38

### PART NUMBER

#### FULL VENEER:

1BSTKNS01005TN - Sold per Ton

#### THIN VENEER:

Qty Bx flat: 1BTVKNS01005QB - Sold per pallet

Sm Bx flat: 1BTVKNS01005BX - Sold per box

Qty Bx corner: 1BTVKNS01505QB- Sold per pallet

Sm Bx corner: 1BTVKNS01505BX- Sold per box

### ARCHITECT/DESIGNER INFO

#### MATERIAL BANK

SKU: SM04015



#### INSTALLATION SHOWN

Mortar: Western W-100

Joint Type: Overgrout

#### BIM DETAILS

Revit, Hatch Patterns,  
Seamless Textures, 3-Part  
Specs, DWGS, SDS,  
Warranty



### FULL VENEER

#### COMMON COVERAGE \*Est.(can vary)

Standard Joint	Drystack	Overgrout
40 square feet / ton	30 ft <sup>2</sup> /ton	50 ft <sup>2</sup> /ton

#### DIMENSIONS

l: 4" to 16"

h: 2" to 10"

w: 3" to 5" (4")

note: product can vary in height from full height to half the total height in one piece

#### TYPICAL BLEND

10 percent installed bedface out;  
stone is snapped at least one face;  
sides may or may not be squared;  
overall appearance of stone will be linear when installed

#### TYPICAL PIECE

Ends random; natural cleft top and bottom;  
split or natural split face, split back;  
most sides more irregular and not square.

### THIN VENEER

#### COMMON COVERAGE PER BOX \*Est.(can vary)

Standard Joint	Drystack	Overgrout
8 & 100 square feet	6 & 75 ft <sup>2</sup>	10 & 110 ft <sup>2</sup>

#### DIMENSIONS

l: 4" to 16"

h: 2" to 10"

w: 3/4" to 1-1/4" (1")

corner return 3" to 6"

note: product can vary in height from full height to half the total height in one piece

#### TYPICAL BLEND

10 percent installed bedface out;  
stone is snapped at least one face;  
sides may or may not be squared;  
overall appearance of stone will be linear when installed

#### TYPICAL PIECE

Ends random; natural cleft top and bottom;  
split or natural split face and sawn back;  
most sides more irregular and not square.