



FIELDLEDGE
WHISPERING PINES
PIONEER BLEND

GEOLOGY: quartzitic sandstone- quarried in USA- quarried in USA

COLOR RANGE

75% Whispering Pines LedgeStone
 25% Whispering Pines Fieldstone

COLOR CONSISTENCY PER PALLET

somewhat consistent

PALLET

FULL VENEER: 4,000 pounds
 THIN VENEER: 10-15 lbs/ft²; Qty Bx or Sm Bx
 Qty Bx-100 sq ft flats and 50 lineal ft corners
 Sm Bx- (24) 8 sq ft flats (192 sq ft) and
 (20) 8 lineal ft corners (160 lineal ft)

ASTM TESTING DATA

WHISPERING PINES C97
 water absorption—0.96%
WHISPERING PINES C97
 specific gravity—2.65
WHISPERING PINES C99
 modulus of rupture—4,550 psi
WHISPERING PINES C170
 compressive strength—11,630 psi
WHISPERING PINES C880
 flexural strength—2,120 psi wet—12,920 psi
 | 11,220 psi
 compressive strength perpendicular
 dry—n/a | 15,300 psi

PART NUMBERS

FULL VENEER:

1BSTCAT01003TN- Sold per Ton

THIN VENEER:

Qty Bx flat: 1BTVCAT01003QB - Sold per pallet
 Sm Bx flat: 1BTVCAT01003BX - Sold per box
 Qty Bx corner: 1BTVCAT01503QB- Sold per pallet
 Sm Bx corner: 1BTVCAT01503BX - Sold per box

FULL VENEER

*Est.(can vary)

COMMON COVERAGE		
Standard Joint	Drystack	Overgrout
40 square feet / ton	30 ft ² /ton	50 ft ² /ton

DIMENSIONS

LEDGESTONE	FIELDSTONE
l: 6" to 24" (12")	3" to 16" dia.
h: 1" to 4"	3" to 16" dia.
w: 3" to 5" (4")	3" to 5" (4")

TYPICAL PIECE

See Whispering Pines LedgeStone and Fieldstone.

THIN VENEER

*Est.(can vary)

COMMON COVERAGE PER BOX		
Standard Joint	Drystack	Overgrout
8 & 100 square feet	6 & 75 ft ²	10 & 110 ft ²

DIMENSIONS

LEDGESTONE	FIELDSTONE
l: 6" to 24" (12")	3" to 16" dia
h: 1" to 4"	3" to 16" dia
w: 3/4" to 1-1/4" (1")	w: 3/4" to 1-1/4" (1")
corner return 3" to 6"	corner 3" to 5"

TYPICAL PIECE

See Whispering Pines LedgeStone and Fieldstone.

ARCHITECT/DESIGNER INFO

MATERIAL BANK

SKU: SM04012



INSTALLATION SHOWN

Mortar: Laticrete MVIS
 Joint Type: Drystack

BIM DETAILS

Revit, Hatch Patterns,
 Seamless Textures, 3-Part
 Specs, DWGS, SDS,
 Warranty



www.buechelstone.com