



**ASHLAR**

**WHITE  
COUNTRY SQUIRE**

**GEOLOGY:** dolomitic limestone- quarried in USA

**COLOR RANGE**

light gray to white

**COLOR CONSISTENCY PER PALLET**

consistent

**PALLET**

FULL VENEER: 4,000 pounds

THIN VENEER: 10-15 lbs/ft<sup>2</sup>; Qty Bx or Sm Bx

Qty Bx-100 sq ft flats and 50 lineal ft corners

Sm Bx- (24) 8 sq ft flats (192 sq ft) and

(20) 8 lineal ft corners (160 lineal ft)

**ASTM TESTING DATA**

FOND DU LAC C97 water absorption—0.11%

FOND DU LAC C97 density—176.5 pcf

FOND DU LAC C99

modulus of rupture—2,480 psi

FOND DU LAC C170

compressive strength w/rift—31,810 psi

compressive strength across rift—26,550 psi

FOND DU LAC C880

flexural strength—1,740 psi

**FULL VENEER**

**COMMON COVERAGE** \*Est.(can vary)

Standard Joint	Drystack	Overgrout
40 square feet / ton	30 ft <sup>2</sup> /ton	50 ft <sup>2</sup> /ton

**DIMENSIONS**

l: 6" to 42" (14")

h: 1/2" to 8"

w: 3" to 5" (4")

Stone ends shall be no less than 2-1/2" width

**TYPICAL PIECE**

Ends square; natural cleft top and bottom; back, face and sides split; stone is mostly rectangular.

**THIN VENEER**

**COMMON COVERAGE PER BOX** \*Est.(can vary)

Standard Joint	Drystack	Overgrout
8 & 100 square feet	6 & 75 ft <sup>2</sup>	10 & 110 ft <sup>2</sup>

**DIMENSIONS**

l: 6" to 24" (12")

h: 1/2" to 8"

w: 3/4" to 1-1/4" (1")

corner return 3" to 5"

**TYPICAL PIECE**

Ends square; natural cleft top and bottom; face and sides split; sawn back; stone is mostly rectangular.

**PART NUMBERS**

**FULL VENEER:**

1BSTBUE02003TN- Sold per Ton

**THIN VENEER:**

Qty Bx flat: 1BTVBUE02003QB - Sold per pallet

Sm Bx flat: 1BTVBUE02003BX- Sold per box

Qty Bx corner: 1BTVBUE02503QB- Sold per box

Sm Bx corner: 1BTVBUE02503BX- Sold per pallet

**ARCHITECT/DESIGNER INFO**

**MATERIAL BANK**

SKU: SM01029



**INSTALLATION SHOWN**

Mortar: Western W-5 (White)

Joint Type: Raked

**BIM DETAILS**

Revit, Hatch Patterns, Seamless Textures, 3-Part Specs, DWGS, SDS, Warranty



www.buechelstone.com