

PATIO & PAVING

CHILTON COLONIAL PAVERS



GEOLOGY: dolomitic limestone

BASIC USE

on patios and walkways; stone is dryset in gravel (screenings) bed or mortared in

COLOR RANGE

purple, lavender, mauve, gray, buff, blue, and brown; white from tumbling

COLOR CONSISTENCY PER PALLET

somewhat consistent

WEIGHT CALCULATED IN INCHES

$l \times w \times h / 1728$ (inches cubed) $\times 170$
= approx 170 pounds per cubic foot

PALLET

4,000 pounds

PATIO & PAVING

CHILTON COLONIAL PAVERS

DIMENSIONS

US: inches

l: 5" or 10"

h: 5"

w: 1", 2", 3", 4", 5"

+/- 1" on height

note: $\pm 1/8"$ on sawn heights

TYPICAL PIECE

ends square;

sawn top and bottom;

sides are split;

bedface face and back;

back may be sawn;

stone rounded from tumbling

PART NUMBERS

part number 5"x5"x1": 1PAVBUE01001TN

part number 5"x5"x2": 1PAVBUE01003TN

part number 5"x5"x3": 1PAVBUE01005TN

part number 5"x5"x4": 1PAVBUE01007TN

part number 5"x 5"x 5": 1PAVBUE01009TN

part number 5"x10"x1": 1PAVBUE01002TN

part number 5"x10"x2": 1PAVBUE01004TN

part number 5"x10"x3": 1PAVBUE01006TN

part number 5"x 10"x 4": 1PAVBUE01008T

part number 5"x 10"x 5": 1PAVBUE01010TN

ASTM TESTING DATA

CHILTON C97 water absorption—0.08%

CHILTON C97 density—177.4 pcf

CHILTON C99 modulus of rupture—1,220 psi

CHILTON C170

compressive strength w/rift—50,560 psi

compressive strength across rift—38,090 psi

CHILTON C880 flexural strength—3,070 psi



www.buechelstone.com